




# Tuff Rib™ Roof & Wall Panel Technical Data Resource

## LAP DETAIL



## ROOF & WALL PROFILE



## KEY FEATURES

- 29 and 26 Tru-Gauge™
- 3:12 minimum pitch recommended when installed with butyl sealant
- Custom lengths 1' to 45'  
*(For longer length panels, please inquire)*
- Long length flashings available up to 20' 11"
- Standard trim, custom trim and accessory packages available
- Color matched neoprene washered screws
- Roof and Vertical or Horizontal Wall application
- Perforated options available *(please inquire)*
- Fiberglass & Polycarbonate panels available to match profile
- Manufactured in Salem OR and Riverside CA
- OverEZee™ retro-fit systems available

## TESTING

- Code compliance UL Evaluation Report  
UL ER #25913-01
- UL 790 Class A (ASTM E108) - Fire rated
- UL 2218 Class 4 - Impact (hail) rated
- ASTM E1680 - Air infiltration (roof)
- ASTM E1646 - Water infiltration (roof)
- ASTM E1592 - Negative structural uniform static air pressure
- ASTM E330 - Positive structural uniform static air pressure
- ASTM E331 - Water infiltration (wall)
- ASTM E283 - Air infiltration (wall)
- ASTM A653/A924 - G90 Galvanized
- ASTM A792 - Zincalume/Galvalume AZ-50/55
- ASTM E455-19 - Shear and Diaphragm.  
*(For engineering data, please inquire)*

## WEIGHT CHART

TUFF RIB	WIDTH	29 GA STEEL	26 GA STEEL
THICKNESS		0.0136"	0.019"
WEIGHT/LINFT	36"	1.917 LBS	2.819 LBS
WEIGHT/SQFT	36"	0.639 LBS	0.940 LBS

ASTM E 1680/E283 Air Penetration	ASTM E 1646/E331 Water Penetration
25 PSF<0.01 CFM/ft <sup>2</sup> -PASS	50 PSF - Pass
Intertek Test Result	Intertek Test Result
Intertek Test Result	



## SHEAR LOAD AND STIFFNESS CHART

Shear load test results for Tuff Rib panels at support spacing of 4' 0"

Test No.	Ga.	Span (ft)	L (ft)	b (ft)	0.4P <sub>max</sub> (lb)	Shear Deflection Δ <sub>n</sub> (in)	Max. Shear Load P <sub>u</sub> (lb)	Ultimate Shear S <sub>u</sub> (lb/ft)	Shear Stiffness G' (lb/in)
1	26	4' 0"	16	15	3848	0.106	9620	641.3	38722
2			16	15	3794	0.095	9486	632.4	42604
Average							9553	636.9	40663
3	29	4' 0"	16	15	2321	0.081	5802	386.8	30562
4			16	15	2287	0.078	5717	381.1	31273
Average							5760	384.0	30917

**Notes:**

P<sub>u</sub> = Maximum applied load in the cantilever beam test (lb)

P = 0.4P<sub>u</sub> in the cantilever beam test (lb)

Δ<sub>n</sub> = Net shear deflection of diaphragm (in) at 0.4P<sub>u</sub> load

G' = Shear stiffness of the diaphragm as determined from test measurements

L = Length of diaphragm test frame = 16 ft

b = Depth of diaphragm test frame = 15 ft